



Characteristic	Standard	Unit	Requirement***	Value From Manufacturing Controls*
Modulus at 10% Elongation	ASTM D412	psi	≥300	455.64
Static Coefficient of Friction (neolite heel)	ASTM D2047	-	≥0.50 (dry)	≥0.80 (dry)
Durometer Hardness	ASTM D2240	Shore A	≥85	95
Abrasion Resistance (H18 wheel, 1000 g, 1000 cycles)	ASTM D3389	g loss	≤1.0	0.22
Critical Radiant Flux	ASTM E648	W/cm ²	≥0.45	≥0.45 (Class 1)
Optical Density of Smoke	ASTM E662	-	≤450	≤450
Wear Layer Thickness	ASTM F410	mm	≥1	Compliant
Chemical Resistance	ASTM F925	-	≤Slight Change	Compliant**
Static Loading	ASTM F970	in	≤0.005 (at 250 psi)	0.001 (tested at 250 psi) 0.004 (tested at 800 psi)
Resistance to Heat	ASTM F1514	ΔE	≤8.0	Compliant
Resistance to Light	ASTM F1515	ΔE	≤8.0	Compliant
Tile Size	ASTM F2055	mm	±0.45	Compliant
Tile Squareness	ASTM F2055	mm	≤0.254	Compliant
Dimensional Stability of Tiles	ASTM F2199	%	≤0.15	Compliant
Resistance to Fungi	ASTM G21	-	-	No Growth
Impact Sound Insulation	ISO 10140-3	dB	-	≈11 (ΔL _w)

Health and Environmental Attributes

Indoor Air Quality (VOC Emissions)	AgBB CA Section 01350 French Decree № 2011-321 GREENGUARD Certification GREENGUARD Gold M1 Emission Class for Building Materials	
Environmental Label	The Blue Angel (RAL-UZ 120) GECA 25-2011v2	
Health-Conscious Production	Kayar is free from red listed ingredients (LBC Red List) and is manufactured <u>without</u> bisphenol A (BPA), formaldehyde, halogens, heavy metals, isocyanates, phthalates and polyvinyl chloride (PVC).	
Materials and Resources (% by Weight)	Pre-consumer recycled content: Rapidly renewable materials:	≥10% ≥4%
Production Plant	ISO 9001 and ISO 14001 Kayar is manufactured from 100% renewable electric energy sources: water, wind and solar.	

Weight and Dimensions	Metric	Imperial
Thickness (ASTM F386)	3 mm (±0.15 mm)	0.118" (±0.006")
Weight	~4.9 kg/m ²	~1.00 lb/ft ²
Rubber Sheet Width	1.90 m	6'2"
Rubber Sheet Length	10 m [min. 6 m; max. 18 m]	32'9" [min. 19'8"; max. 59']
Rubber Tile Size	61 cm x 61 cm	24" x 24"

*Values obtained from manufacturing controls can vary between production lots and do not constitute representations or warranties as to any particular production lot. Mondo reserves the right to modify product design and/or specifications at any time without notice.

**For the complete list of chemicals tested, concentrations and contact time, please communicate with Mondo's Technical Department.

*****WARNING ON REQUIREMENTS: MINIMAL REQUIREMENT TO BE RESPECTED AT ALL TIMES.**